

# Woven PTFE-Coated Fiberglass 6230

Expanded PTFE Membrane on Woven PTFE-Coated Fiberglass



Fiber	Fiberglass
Yarn Type	
Warp	37 1/0; 37 1/0 Tex
Fill	75 1/3 Tex
Finish (Base Fabric)	PTFE
Weight (Nominal)	16.8 oz/yd <sup>2</sup> 570 g/m <sup>2</sup>
Weave Pattern	Double-beam; Modified Crowfoot
Thread Count	48 x 30 (Warp x Fill)
Air Permeability (Average)	6.0 cfm/ft <sup>2</sup> @ 0.5" wg 2.9 (m <sup>3</sup> /min/m <sup>2</sup> @ 20 mm wg)
Continuous Service Temperature	500°F 260°C
Mullen Burst Strength	600 psi 4137 kilopascals
Breaking Strength	
Warp	325 Lbf/1" modified cut strip 1446 N/2.54 cm modified cut strip
Fill	300 Lbf/1" modified cut strip 1334 N/2.54 cm modified cut strip

To place an order or to learn more about PRISTYNE® Filter Media, please contact us:

**By telephone**

+49 89 4612 - 22 48 (Europe)  
+86 21 5172 8299 (China)  
+1 800 542 2434 (US)

**By fax**

+49 89 4612 - 23 08 (Europe)  
+86 21 6247 9199 (China)  
+410 506 3463 (US)

**By e-mail**

sales@pristyne.com

**On the Web**

www.pristyne.com

**W.L.Gore & Associates**

101 Lewisville Road  
Elkton, MD 21922  
USA

All data expressed as typical values. This specification is subject to change. Please contact PRISTYNE® Media Group directly to confirm current information.

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

