

# PPS Felt with RASTEX® Scrim 4220

Expanded PTFE Membrane on PPS Felt with RASTEX® Scrim



Fiber	100% Polyphenylene Sulfide (PPS)
Scrim	Woven RASTEX® Monofilament Yarn
Finish (Base Fabric)	N/A
Weight (Nominal)	16.0 oz/yd <sup>2</sup> 542 gm/m <sup>2</sup>
Air Permeability (Average)	4.5 cfm/ft <sup>2</sup> @ 0.5" wg 2.2 m <sup>3</sup> /min/m <sup>2</sup> @ 20 mm wg
Continuous Service Temperature	375°F 190°C
Mullen Burst Strength	500 psi (minimum average) 3447 kilopascals
Breaking Strength	
Warp	125 Lbf/2" (minimum average) 555 N/5 cm
Fill	150 Lbf/2" (minimum average) 665 N/5 cm

To place an order or to learn more about PRISTYNE® Filter Media, please contact us:

#### By telephone

+49 (0) 89 4612 - 22 48 (Europe)

+86 21 6247 1999 (China)

+1 800 542 2434 (US)

#### By fax

+49 (0) 89 4612 - 23 08 (Europe)

+86 21 6247 9199 (China)

+410 506 3463 (US)

#### By e-mail

sales@pristyne.com

#### On the Web

www.pristyne.com

#### W. L. Gore & Associates

101 Lewisville Road

P.O. Box 917

Elkton, MD 21922

USA

All data expressed as typical values.  
This specification is subject to change.  
Please contact PRISTYNE® Media Group  
directly to confirm current information.

