

Acid-Resistant Aramid/Felt 475 g/m² (14 oz/yd²)

# FILTER CARTRIDGES

## DESCRIPTION

A 204 °C (400 °F) maximum service temperature, stayed-aramid felt filter cartridge for use in pulse jet style dust collectors where high differential pressure and high cleaning pressures are required due to aggressive dust loading.

#### **FEATURES & BENEFITS**

- GORE<sup>™</sup> membrane technology provides an excellent combination of filtration efficiency and dust cake release.
- Polytetrafluoroethylene scrim offers superior chemical resistance and excellent dimensional stability.
- Unique acid-resistant treatment reduces the detrimental effects of moisture and acids.
- Withstands pressure drop up to 6.2 kPa (25 inches water gauge).
- Available in top, bottom, and horizontal loading configurations.

### Applications

- **Chemicals Processing:** Dryers, bin vents, and nuisance dust collectors in the pigment, plastic, and catalyst industries.
- Minerals Processing: Clinker coolers.
- **Metals Processing:** Process venting dust collectors for base metal kiln applications.

#### LAMINATE TECHNICAL DATA

Weight	475 g/m <sup>2</sup> (14 oz/yd <sup>2</sup> )
Fiber Content	100 % Virgin Aramid
Felt Construction	Supported Needlefelt with Acid-Resistant Treatment
Continuous Operating Temperature	204 °C (400 °F)
Maximum Surge Temperature	218 °C (425 °F)
Acid Resistance	Very Good
Alkali Resistance	Good
Breaking Strength	
• Warp	1112 N/5 cm (250 lb/2 in) wide sample
• Fill	1600 N/5 cm (360 lb/2 in) wide sample
Mullen Burst	4653 kPa (675 psi)
Thickness	1.91 mm (0.075 in)
Elongation at 50 lb	
• Warp	2.0 %
• Fill	5.5 %
Flame-Resistance Testing ASTMD 6413-08	
• After Flame	0 seconds
• After Glow	35.1 seconds
• Char Length	1.1 inches

Note: All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging options. GORE and designs are trademarks of W. L. Gore & Associates ©2011–2017 W. L. Gore & Associates, Inc.



