

GORE® DeNOx CATALYTIC FILTER BAGS

Needle Felt 1320 g/m² (39 oz/yd²)

Description

GORE® DeNOx Catalytic Filter Bags reduce NO_x and NH₃ with minimum or no changes in the existing process and equipment.

Features & Benefits

- Reliably meet NO_x, NH₃ and particulate compliance requirements
- Low capital investment
- Minor or no changes to process and operation
- No additional footprint
- No differential pressure increase
- Minimum downtime for installation

Applications

- Waste-to-Energy
- Chemicals processing
- Lime and cement
- Metals processing

Laminate Technical Data

Fiber Content	Staple – PTFE Scrim – Woven PTFE
Felt Construction	Supported Needlefelt
Continuous Operating Temperature	500 °F (260 °C) maximum
Maximum Surge Temperature	525 °F (274 °C)
Acid Resistance	Excellent
Alkali-Resistance	Excellent
Weight	39 oz/yd ² (1320 g/m ²)
Breaking Strength	Machine Direction: 120 lbs/2" wide sample (53 kg/5 cm) Cross-Machine Direction: 130 lbs/2" wide sample (58 kg/5 cm)
Mullen Burst	400 psi (28 kg/cm ²)
Thickness	0.072" (1.85 mm)
Thermal Stability	Less than 4% shrinkage at 260 °C after 2 hours (on cage)
Durability	Excellent

Product attributes expressed as minimum values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, *Together, improving life* and designs are trademarks of W. L. Gore & Associates. © 2020–2025 W. L. Gore & Associates, Inc.