



## GORE® GR Sheet Gasketing

Exceptionally resistant to creep, cold flow and aggressive media, this 100% ePTFE gasket sheet reliably seals steel piping and equipment.

### Technical Specifications

#### Material

100% ePTFE (expanded polytetrafluoroethylene), with multidirectional strength.

#### Operating range

The maximum applicable pressure and temperature depend mainly on the equipment and installation.

**Typical use:** -60 °C to 230 °C (-76 °F to 446 °F);  
industrial full vacuum<sup>1</sup> to 40 bar (580 psi).

**Maximum use:** -269 °C to 315 °C (-452 °F to 600 °F);  
full vacuum to 210 bar (3000 psi).

For applications outside the typical use range, Gore recommends an application-specific engineering design calculation and extra care during installation. Also, consider retorquing after a thermal cycle when the equipment has returned to an ambient temperature condition. Please contact Gore if further guidance is required.

#### Chemical resistance

Chemical resistance to all media pH 0–14, except molten alkali metals and elemental fluorine.

#### Shelf life

ePTFE is not subject to aging and can be stored indefinitely.

#### Food Contact

Suitable for food contact applications.\*

### Certifications & Application Information

TA Luft, Oxygen Service (BAM), Chlorine Service, Marine & Offshore Applications (ABS), Leachable Fluoride and Chloride, Blowout VDI2200, ISO 9001 and Food Contact.

Further information, including certificates and safety information, is available on [gore.com/sealants](http://gore.com/sealants).

### Product Sizes

GORE® GR Sheet Gasketing is available in 1524 x 1524 mm (60" x 60") sheet. Standard thicknesses range from 1 mm (1/32") up to 6.0 mm (1/4"). Other sheet thicknesses may be available upon request. For applications where ink is not acceptable, embossed sheet is available.

| Thickness      | 1.0 mm<br>(1/32") | 1.5 mm<br>(1/16") | 3.0 mm<br>(1/8") | 6.0 mm<br>(1/4") |
|----------------|-------------------|-------------------|------------------|------------------|
| Printed Sheet  | ✓                 | ✓                 | ✓                | ✓                |
| Embossed Sheet |                   | ✓                 | ✓                | ✓                |

### Technical Information

#### Gasket design factors

The sealability of a bolted flange connection depends upon a number of variables associated with the flange, bolt, gasket, and application-specific operating conditions.

EN 13555 provides the test method for generating the gasket parameters used in EN 1591-1 calculations. The resulting gasket parameters ( $Q_{\min}$ ,  $Q_{S\min}$ ,  $Q_{S\max}$ ,  $P_{QR}$ ,  $E_G$ ) are dependent on the selected test conditions. Users should select the values that best match their application. For complete EN 13555 data, please visit [gore.com/sealants](http://gore.com/sealants).

$m$  &  $y$  are gasket constants used for flange design as specified in the ASME Boiler and Pressure Vessel Research Code Division 1 Section VIII Appendix 2. See the table on the next page for results.

AD 2000 B 7 gasket parameters are available on [gore.com/sealants](http://gore.com/sealants).

<sup>1</sup> Absolute pressure of 1 mmHg (Torr) = 133 Pa = 1.33 mbar = 0.019 psi

## Technical Data: GORE® GR Sheet Gasketing

|                                                                                                                 |                 | Thickness                                                      |                                                                |                                                                | Test conditions       |                 |                       |
|-----------------------------------------------------------------------------------------------------------------|-----------------|----------------------------------------------------------------|----------------------------------------------------------------|----------------------------------------------------------------|-----------------------|-----------------|-----------------------|
|                                                                                                                 |                 | 1.5 mm (1/16")                                                 | 3.0 mm (1/8")                                                  | 6.0 mm (1/4")                                                  | Gasket stress         | Temperature     | Pressure              |
| Sealability                                                                                                     |                 |                                                                |                                                                |                                                                |                       |                 |                       |
| Q <sub>min</sub> (L <sub>0.1</sub> )<br>Q <sub>min</sub> (L <sub>0.01</sub> )<br>Q <sub>Smin</sub> <sup>2</sup> |                 | 19 MPa (2,760 psi)<br>32 MPa (4,640 psi)<br>10 MPa (1,450 psi) | 24 MPa (3,480 psi)<br>37 MPa (5,365 psi)<br>10 MPa (1,450 psi) | 29 MPa (4,205 psi)<br>41 MPa (5,950 psi)<br>10 MPa (1,450 psi) | Variable <sup>3</sup> | Room            | 40 bar (580 psi)      |
| m & y                                                                                                           |                 | 2.5 & 19.3 MPa (2,800 psi)                                     |                                                                |                                                                | Variable <sup>4</sup> | Room            | Variable <sup>4</sup> |
| ASTM F37-95                                                                                                     |                 | 0.3 ml/h <sup>5</sup>                                          |                                                                |                                                                | 20.7 MPa (3,000 psi)  | Room            | 2 bar (30 psi)        |
| ARLA                                                                                                            | Before<br>After | 1.04E-04 mg/s<br>1.42E-05 mg/s                                 | 1.04E-03 mg/s<br>< 1.0E-7 mg/s                                 | –                                                              | 34.5 MPa (5,000 psi)  | 315 °C (600 °F) | 55 bar (800 psi)      |
| ROTT                                                                                                            | Gb<br>a<br>Gs   | 685 psi<br>0.271<br>6.19E-02 psi                               | 770 psi<br>0.274<br>9.38E-07 psi                               | –                                                              | Variable <sup>6</sup> | Room            | Variable <sup>6</sup> |
| Relaxation                                                                                                      |                 |                                                                |                                                                |                                                                |                       |                 |                       |
| P <sub>QR</sub> <sup>3</sup>                                                                                    |                 | 0.90                                                           | 0.85                                                           | 0.79                                                           | 20 MPa (2,900 psi)    | Room            | –                     |
|                                                                                                                 |                 | 0.94                                                           | 0.90                                                           | 0.84                                                           | 30 MPa (4,350 psi)    |                 |                       |
|                                                                                                                 |                 | 0.98                                                           | 0.95                                                           | 0.90                                                           | 50 MPa (7,250 psi)    |                 |                       |
|                                                                                                                 |                 | 0.61                                                           | 0.47                                                           | 0.39                                                           | 20 MPa (2,900 psi)    | 150 °C (302 °F) | –                     |
|                                                                                                                 |                 | 0.87                                                           | 0.73                                                           | 0.58                                                           | 30 MPa (4,350 psi)    |                 |                       |
|                                                                                                                 |                 | 0.96                                                           | 0.78                                                           | 0.62                                                           | 50 MPa (7,250 psi)    |                 |                       |
|                                                                                                                 |                 | 0.58                                                           | 0.37                                                           | 0.25                                                           | 20 MPa (2,900 psi)    | 230 °C (446 °F) | –                     |
|                                                                                                                 |                 | 0.89                                                           | 0.75                                                           | 0.52                                                           | 30 MPa (4,350 psi)    |                 |                       |
|                                                                                                                 | 0.86            | 0.65                                                           | 0.51                                                           | 50 MPa (7,250 psi)                                             |                       |                 |                       |
| ASTM F38-95                                                                                                     |                 | 23% <sup>7</sup>                                               |                                                                |                                                                | 20.7 MPa (3,000 psi)  | 100 °C (212 °F) | –                     |
| ARLA                                                                                                            |                 | 31%                                                            | 43%                                                            | –                                                              | 34.5 MPa (5,000 psi)  | 315 °C (600 °F) | –                     |
| Crush strength                                                                                                  |                 |                                                                |                                                                |                                                                |                       |                 |                       |
| Q <sub>Smax</sub> <sup>3</sup>                                                                                  |                 | 230 MPa (33,360 psi)                                           | 230 MPa (33,360 psi)                                           | 160 MPa (23,205 psi)                                           | –                     | Room            | –                     |
| ROTT                                                                                                            |                 | 276 MPa (40,030 psi)                                           | 276 MPa (40,030 psi)                                           | –                                                              | –                     | Room            | –                     |
| Compressibility                                                                                                 |                 |                                                                |                                                                |                                                                |                       |                 |                       |
| ASTM F36-99                                                                                                     |                 | 56% <sup>5</sup>                                               |                                                                |                                                                | 17.2 MPa (2,500 psi)  | Room            | –                     |
| Recovery                                                                                                        |                 |                                                                |                                                                |                                                                |                       |                 |                       |
| ASTM F36-99                                                                                                     |                 | 8% <sup>5</sup>                                                |                                                                |                                                                | 17.2 MPa (2,500 psi)  | Room            | –                     |
| Blowout                                                                                                         |                 |                                                                |                                                                |                                                                |                       |                 |                       |
| VDI 2200 (06-2007)                                                                                              |                 | Pass Step 1 <sup>8</sup> / Pass Step 2 <sup>8</sup>            |                                                                |                                                                | 30 MPa (4,350 psi)    | 230 °C (446 °F) | 50 bar (725 psi)      |
| HOBT with cycling                                                                                               |                 | Trial gasket temperature 315 °C (600 °F) <sup>8</sup>          |                                                                |                                                                | 34.5 MPa (5,000 psi)  | –               | 30 bar (435 psi)      |

<sup>2</sup> Up to  $L_{0.001}$  and  $Q_A > 40$  MPa

<sup>3</sup> Tested per EN 13555

<sup>4</sup> Tested per Standard Practice ASTM F-3149-15

<sup>5</sup> Tested thickness 1.5 mm (1/16")

<sup>6</sup> Tested per ROTT Draft 9 Soft Gasket Test Procedure

<sup>7</sup> Tested thickness 0.8 mm (0.03")

<sup>8</sup> Tested thickness 3.0 mm (1/8")

**\*GORE® GR Sheet Gasketing meets the requirements for repeat-use food contact applications with all food types per FDA regulations 21CFR174.5 (d) (1-5), 21CFR177.1550 (and 21 CFR175.300 for products with red and green printing ink) and conform to the requirements of regulation (EC) No 1935/2004 including (EU) No 10/2011. Declaration of Compliance is available upon request.**

All technical information and advice given here is based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, *Together, improving life* and designs are trademarks of W. L. Gore & Associates. © 2017–2025 W. L. Gore & Associates GmbH

**PLEASE VISIT GORE.COM/SEALANTS TO FIND CONTACT DETAILS FOR ALL LOCAL SALES OFFICES.**

### North America / South America

**W. L. Gore & Associates, Inc.**

**(USA)**

**T +1 800 654 4229**

**F +1 410 506 8585**

**E sealants@wlgore.com**

### Europe / Middle East / Russia / Africa

**W. L. Gore & Associates GmbH**

**(Germany)**

**T +49 89 4612 2215**

**F +49 89 4612 43780**

**E sealants\_EU@wlgore.com**

### Asia / Australia

**W. L. Gore & Associates Technologies**

**(Shenzhen) Co., Ltd. Shanghai Branch**

**T +86 21 5172 8299**

**F +86 21 6247 9199**

**E sealants\_AP@wlgore.com**

