# GORE® HIGH DURABILITY FILTER BAG

Anti-Static Polyester Felt 475 g/m<sup>2</sup> (14 oz/yd<sup>2</sup>)

## Description

A 135 °C (275 °F) maximum service temperature, anti-static polyester fe lt filter bag for use in pulse jet style dust collectors where static dissipation is required.

#### Features & Benefits

- GORE High Durability membrane technology provides an excellent combination of filtration efficiency, airflow, and durability.
- Polyester fibers provide good all-around chemical resistance, especially in applications operated below 79 °C (175 °F).
- Special multifilament scrim design provides excellent dimensional stability and resistance to mechanical damage over the life of the filter.
- Also available in cartridge form with top, bottom, and horizontal loading configurations. Withstands pressure drop up to 6.2 kPa (25 inches of water gauge)

## **Applications**

**Chemicals Processing:** Dryer baghouses, bin vents, and nuisance dust collectors in the catalyst, pigment, and plastic industries.

Minerals Processing: Coal mill collectors.

**Metals Processing:** Process venting and material handling dust collectors for pulverized coal.

**Power Generation and Incineration:** Coal handling collectors and coal milling baghouses.

### Laminate Technical Data

Weight	475 g/m² (14 oz/yd²)
Fiber Content	Polyester fiber with polyester and stainless steel scrim
Felt Construction	Supported Needlefelt
Continuous Operating Temperature	135 °C (275 °F)
Maximum Surge Temperature	149 °C (300 °F)
Acid Resistance	Fair
Alkali Resistance	Fair
Breaking Strength	Warp: 1334 N/5 cm (300 lb/2 in) wide sample Fill: 1557 N/5 cm (350 lb/2 in) wide sample
Mullen Burst	4481 kPa (650 psi)
Antistatic Performance	<10 <sup>8</sup> Ohm DIN 54345

All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, Together, improving life and designs are trademarks of W. L. Gore & Associates. © 2011–2025 W. L. Gore & Associates, Inc.

