GORE® HIGH DURABILITY FILTER BAG

PTFE Felt 830 g/m² (24.5 oz/yd²)

Description

A 260 °C (500 °F) maximum service temperature, PTFE felt filter bag for use in pulse jet style dust collectors with chemically aggressive operating conditions.

Features & Benefits

- GORE High Durability membrane technology provides an excellent combination of filtration efficiency, airflow, and durability.
- Chemically inert providing the highest all-around chemical resistance and maximum bag life.
- Constructed using a woven PTFE scrim that provides excellent dimensional stability, extended flex life, and resistance to mechanical damage over the life of the filter.

Applications

Chemicals Processing: Chemical process reactors that incorporate micronizing, grinding, and product collection in extreme environments that are chemically and thermally aggressive.

Minerals Processing: Brick kilns.

Metals Industry: Lead, copper, and other base metal production.

Power Generation and Incineration: Medical and municipal waste incineration, as well as coal-fired boilers.

Laminate Technical Data

Weight	830 g/m² (24.5 oz/yd²)
Fiber Content	Staple – PTFE
	Scrim – Woven PTFE
Felt Construction	Supported Needlefelt
Continuous Operating Temperature	260 °C (500 °F)
Maximum Surge Temperature	274 °C (525 °F)
Acid Resistance	Excellent
Alkali Resistance	Excellent
Breaking Strength	Warp: 890 N/5 cm (200 lb/2 in) wide sample
	Fill: 824 N/5 cm (185 lb/2 in) wide sample
Mullen Burst	4136 kPa (600 psi)
Thermal Stability	< 2 % shrinkage at 260 °C (500 °F) after 2 hours unrestrained)
Durability	Very good
	· · · · · · · · · · · · · · · · · · ·

All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, Together, improving life and designs are trademarks of W. L. Gore & Associates. © 2011–2025 W. L. Gore & Associates, Inc.

