

GORE® HIGH DURABILITY FILTER CARTRIDGE

Polyester Felt 407 g/m² (12 oz/yd²)

Description

A 135 °C (275 °F) maximum service temperature, stayed-polyester felt filter cartridge for use in pulse jet style dust collectors where high differential pressure and high cleaning pressures are required due to aggressive dust loading.

Features & Benefits

- GORE High Durability membrane technology provides an excellent combination of filtration efficiency, airflow, and durability.
- Polyester fibers provide good all-around chemical resistance, especially in applications operated below 79 °C (175 °F).
- Available in top, bottom, and horizontal loading configurations.
- Withstands pressure drop up to 6.2 kPa (25 inches water gauge).

Applications

Chemicals Processing: Dryers, bin vents, and nuisance dust collectors in the pigment, plastic, and catalyst industries.

Minerals Processing: Finish mill, bulk loading, ship off-loaders, and bin vent dust collectors.

Metals Processing: Material handling for coal and limestone. Process venting dust collectors in the lead, lead oxide, and iron and steel industries. Fume and bulk handling systems in coke production, and sand reclamation systems in foundries.

Laminate Technical Data

Weight	407 g/m ² (12 oz/yd ²)
Fiber Content	Polyethylene Terephthalate
Felt Construction	Supported Needlefelt
Continuous Operating Temperature	135 °C (275 °F)
Maximum Surge Temperature	149 °C (300 °F)
Acid Resistance	Fair
Alkali Resistance	Fair
Breaking Strength	601 N/5 cm (135 lb/2 in) wide sample 890 N/5 cm (200 lb/2 in) wide sample
Mullen Burst	2068 kPa (300 psi)

All data expressed as minimum values. This specification is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, *Together, improving life* and designs are trademarks of W. L. Gore & Associates. © 2010–2025 W. L. Gore & Associates GmbH