

# GORE® LOW DRAG FILTER BAGS

PTFE Fabric 288 g/m<sup>2</sup> (8.5 oz/yd<sup>2</sup>)

## Description

A 260 °C (500 °F) maximum service temperature, PTFE fabric for use in pulse jet, reverse air, and shaker style dust collectors with chemically aggressive operating conditions.

## Features & Benefits

- The GORE LOW DRAG Filter membrane can be operated at a lower differential pressure (dP), resulting in fan energy savings, longer bag life and improved process control. Some customers choose to operate at a higher airflow (same dP) resulting in potential increases in production capacity or more effective evacuation. In all cases, this membrane provides excellent particulate capture efficiency, dust cake release and filtration performance.

- The backing material is chemically inert and extremely supple and flexible. These features offer enhanced flex life and long bag performance life, even in chemically aggressive conditions.
- PTFE high tenacity sewing thread means a more rugged, dependable construction, which matches the chemical resistance of the rest of the bag.
- Optimized construction brings the best properties of the filter materials together into a finished product where the strength of the design matches and enhances the strength of the components.

## Applications

**Chemicals Industry:** Glass furnaces and Carbon Black.

**Energy Production:** Chemical and hazardous waste incinerators.

**Metals Industry:** Lead, other base metals smelters and furnaces.

## Laminate Technical Data

Weight	288 g/m <sup>2</sup> (8.5 oz/yd <sup>2</sup> )
Fiber Content	PTFE
Continuous Operating Temperature	260 °C (500 °F)
Maximum Surge Temperature	274 °C (525 °F)
Acid Resistance	Excellent
Alkali Resistance	Excellent
Breaking Strength	Warp: 1334 N/2.54 cm (300 lb/1 in) modified grab Fill: 1223 N/2.54 cm (275 lb/1 in) modified grab
Mullen Burst	3447 kPa (500 psi)

All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, *Together, improving life* and designs are trademarks of W. L. Gore & Associates. © 2019–2025 W. L. Gore & Associates GmbH