



GORE® Membrane Filter Socks

Polypropylene Felt
441 g/m² (13 oz/yd²)

DESCRIPTION

The strongest membrane laminate filter sock used in tubular backpulse filters. It is constructed with the membrane on the outside allowing for superior filtration, excellent cake release properties, and minimal backwash volume.

FEATURES & BENEFITS

- Patented GORE™ High Durability Membrane technology provides an excellent combination of filtration efficiency, liquid flow, and durability.
- Available in either of two GORE™ High Durability Membranes. A 0.5 micron and a 1.0 micron nominally rated membrane.

APPLICATIONS

- Acid Waste Water
- Powdered Metals
- Brine Filtration without any Free Chlorine
- Pigments
- Specialty and Fine Chemicals
- Catalyst Recovery

LAMINATE TECHNICAL DATA

Weight	441 g/m ² (13 oz/yd ²)
Fiber Content	Staple: Polypropylene Scrim: Polypropylene Ribbon
Felt Construction	Supported Needlefelt
Retention Efficiency	0.5 micron membrane: > 99% removal of 0.5 micron particles (per ASTM F795-88) 1.0 micron membrane: > 99% removal of 1.0 micron particles (per ASTM F795-88)
Acid Resistance	Excellent
Alkali Resistance	Excellent
Breaking Strength	
• Machine Direction	667 N/5 cm (150 lb/2 in) wide sample
• Cross-Machine Direction	890 N/5 cm (200 lb/2 in) wide sample
Mullen Burst	2068 kPa (300 psi)
Thickness	1.91 mm (0.075 in)

Note: All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging options.

GORE and designs are trademarks of W. L. Gore & Associates © 2013–2018 W. L. Gore & Associates, Inc.

W. L. Gore & Associates, Inc.

101 Lewisville Road, Elkton, MD 21921

US Toll-Free: 800.437.5427 • Phone: +1.410.506.3560

Fax: +1.410.506.0107 • E-mail: performancesolutions@wlgore.com

gore.com/filtration

