## **GORE® Filtration Products**

Data Sheet

# GORE® FILTER BAG

Polyphenylene Sulfide Felt 543 g/m<sup>2</sup> (16 oz/yd<sup>2</sup>)

## Description

A 190 °C (375 °F) maximum service temperature, polyphenylene sulfide felt filter bag for use in pulse jet style dust collectors subject to chemical attack.

#### Features & Benefits

- Patented GORE High Durability membrane technology provides an excellent combination of filtration efficiency, airflow, and durability.
- Polyphenylene sulfide felt has excellent chemical resistance for longer bag life.

## **Applications**

- Power Generation and Incineration: Incinerator baghouses and coal-fired boiler baghouses.
- Chemicals Processing: Dryer baghouses in the pigment, plastic, and catalyst industries.
- Metals Processing: Baghouses in the foundry, base metal production, and EAF steel production industries.

### Laminate Technical Data

Weight 543 g/m² (16 oz/yd²)  Fiber Content Staple – Polyphenylene Sulfide Scrim – Polyphenylene Sulfide Felt Construction Supported Needlefelt  Maximum Continuous Operating Temperature 190 °C (375 °F)  Acid Resistance Excellent  Alkali Resistance Excellent  Breaking Strength Warp: 670 N/5 cm (150 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample  Mullen Burst >2760 kpa or 400 psi  Thickness 1.7–2.3 mm or 0.07"–0.09"  Thermal Stability <2.0% shrinkage at 204 °C (400 °F) for 2 hours  Durability Good		
Fiber Content  Scrim – Polyphenylene Sulfide  Felt Construction  Supported Needlefelt  Maximum Continuous Operating Temperature  190 °C (375 °F)  Acid Resistance  Excellent  Alkali Resistance  Breaking Strength  Warp: 670 N/5 cm (150 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample  Mullen Burst  >2760 kpa or 400 psi  Thickness  1.7–2.3 mm or 0.07"–0.09"  Thermal Stability  <2.0% shrinkage at 204 °C (400 °F) for 2 hours	Weight	543 g/m² (16 oz/yd²)
Maximum Continuous Operating Temperature  Acid Resistance  Excellent  Alkali Resistance  Breaking Strength  Warp: 670 N/5 cm (150 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample  Mullen Burst  >2760 kpa or 400 psi Thickness  1.7–2.3 mm or 0.07"–0.09"  Thermal Stability  < 2.0% shrinkage at 204 °C (400 °F) for 2 hours	Fiber Content	
Acid Resistance Excellent  Alkali Resistance Excellent  Breaking Strength Warp: 670 N/5 cm (150 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample  Mullen Burst >2760 kpa or 400 psi  Thickness 1.7–2.3 mm or 0.07"–0.09"  Thermal Stability <2.0% shrinkage at 204 °C (400 °F) for 2 hours	Felt Construction	Supported Needlefelt
Alkali Resistance Excellent  Breaking Strength Warp: 670 N/5 cm (150 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample  Mullen Burst >2760 kpa or 400 psi  Thickness 1.7–2.3 mm or 0.07"–0.09"  Thermal Stability <2.0% shrinkage at 204 °C (400 °F) for 2 hours	Maximum Continuous Operating Temperature	190 °C (375 °F)
Breaking Strength  Warp: 670 N/5 cm (150 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample  Mullen Burst  >2760 kpa or 400 psi  Thickness  1.7-2.3 mm or 0.07"-0.09"  Thermal Stability  <2.0% shrinkage at 204 °C (400 °F) for 2 hours	Acid Resistance	Excellent
Fill:       1020 N/5 cm (230 lb/2 in) wide sample         Mullen Burst       >2760 kpa or 400 psi         Thickness       1.7-2.3 mm or 0.07"-0.09"         Thermal Stability       <2.0% shrinkage at 204 °C (400 °F) for 2 hours	Alkali Resistance	Excellent
Thickness 1.7–2.3 mm or 0.07"–0.09"  Thermal Stability <2.0% shrinkage at 204 °C (400 °F) for 2 hours	Breaking Strength	·
Thermal Stability <2.0% shrinkage at 204 °C (400 °F) for 2 hours	Mullen Burst	>2760 kpa or 400 psi
•	Thickness	1.7-2.3 mm or 0.07"-0.09"
Durability Good	Thermal Stability	<2.0% shrinkage at 204 °C (400 °F) for 2 hours
	Durability	Good

All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, Together, improving life and designs are trademarks of W. L. Gore & Associates. © 2012–2020 W. L. Gore & Associates, Inc.

