

GORE® LOW DRAG FILTER BAG

Polytetrafluoroethylene Felt 830 g/m² (24.5 oz/yd²)

Description

A 260 °C (500 °F) maximum service temperature, expanded polytetrafluoroethylene felt filter bag for use in pulse jet style dust collectors with chemically aggressive operating conditions.

Features & Benefits

- GORE® LOW DRAG Filter Membrane technology provides an excellent combination of filtration efficiency, airflow, and durability compared to other industry leading membranes.
- Potential benefits of this new technology are longer bag life, higher product throughput or fan energy savings or some combination thereof, depending on the application.
- Woven ePTFE scrim for outstanding dimensional stability, extended flex life, and resistance to mechanical damage. All PTFE construction provides highest all-around chemical resistance and maximum bag life.

Applications

- **Chemicals Processing:** Chemical process reactors that incorporate micronizing, drying, grinding, and product collection in extreme environments that are chemically and thermally aggressive.
- **Minerals Processing:** Brick kilns.
- **Metals Processing:** Lead, copper, and other base metal production.
- **Power Generation and Incineration:** Medical and municipal waste incineration; coal-fired boilers.

Laminate Technical Data

Weight	830 g/m ² (24.5 oz/yd ²)
Fiber Content	Staple – Polytetrafluoroethylene Scrim – Woven Polytetrafluoroethylene
Felt Construction	Supported Needlefelt
Continuous Operating Temperature	260 °C (500 °F)
Maximum Surge Temperature	274 °C (525 °F)
Acid Resistance	Excellent
Alkali Resistance	Excellent
Breaking Strength	Warp: 890 N/5 cm (200 lb/2 in) wide sample Fill: 824 N/5 cm (185 lb/2 in) wide sample
Mullen Burst	4136 kPa (600 psi)
Thickness	1.07 mm (0.042 in)
Thermal Stability (unrestrained)	<2.0% shrinkage at 260 °C (500 °F) after 2 hours
Durability	Very Good

All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, *Together, improving life* and designs are trademarks of W. L. Gore & Associates. © 2021 W. L. Gore & Associates, Inc.

