

## GORE® Filtration Products

Data Sheet

# GORE® LOW DRAG FILTER BAG

Polyphenylene Sulfide Felt 543 g/m<sup>2</sup> (16 oz/yd<sup>2</sup>)

## Description

A 190 °C (375 °F) maximum service temperature, polyphenylene sulfide felt filter bag for use in pulse jet style dust collectors subject to chemical attack.

## Features & Benefits

- The GORE® LOW DRAG Filter Membrane provides an excellent combination of filtration efficiency, airflow, and durability compared to other industry leading membranes.
- Potential benefits of this new technology are longer bag life, higher product throughput or fan energy savings or some combination thereof, depending on the application.
- Polyphenylene sulfide felt has excellent chemical resistance for longer bag life.

## Applications

- **Power Generation and Incineration:** Incinerator baghouses and coal-fired boiler baghouses.
- **Chemicals Processing:** Dryer baghouses in the pigment, plastic, and catalyst industries.
- **Metals Processing:** Baghouses in the foundry, base metal production, and EAF steel production industries.

## Laminate Technical Data

Weight	543 g/m <sup>2</sup> (16 oz/yd <sup>2</sup> )
Fiber Content	Staple – Polyphenylene Sulfide Scrim – Polyphenylene Sulfide
Felt Construction	Supported Needlefelt
Maximum Continuous Operating Temperature	190 °C (375 °F)
Acid Resistance	Excellent
Alkali Resistance	Excellent
Breaking Strength	Warp: 670 N/5 cm (150 lb/2 in) wide sample Fill: 1020 N/5 cm (230 lb/2 in) wide sample
Mullen Burst	>2760 kpa or 400 psi
Thickness	1.7–2.3 mm or 0.07"–0.09"
Thermal Stability	<2.0% shrinkage at 204 °C (400 °F) for 2 hours
Durability	Good

All data expressed as typical values. This technical data is subject to change. Please contact W. L. Gore & Associates, Inc., directly to confirm current information.

### FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

All technical information and advice given here are based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes. Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE, *Together, improving life* and designs are trademarks of W. L. Gore & Associates. © 2023 W. L. Gore & Associates, Inc.